

FIBRANOR IGNIFUGO NAF

TECHNICAL DATA-AVERAGE VALUES

Rev: 14/11/2017

PROPERTIES	TEST METHOD	UNITS	THICKNESSES mm
			5 - <7
DENSITY (*)	EN 323	kg/m ³	870
INTERNAL BOND	EN 319	N/mm ²	0.65
BENDING STRENGTH	EN 310	N/mm ²	23
MODULUS OF ELASTICITY	EN 310	N/mm ²	2700
THICKNESS SWELLING 24 H	EN 317	%	30
DIMENSIONAL MOVEMENT LENGTH/WIDTH	EN 318	%	0.5
DIMENSIONAL MOVEMENT THICKNESS	EN 318	%	7
SURFACE SOUNDNESS	EN 311	N/mm ²	1.2
SURFACE ABSORPTION (TWO FACES)	EN 382-1	mm	> 150
MOISTURE CONTENT	EN 322	%	7+/-3
REACTION TO FIRE	EN 13501-1	Euroclass	B-s1,d0
SOUND ABSORPTION COEFFICIENT (A) (250 A 500 HZ)	EN 13984:2004+A1:2015	α	0,10
SOUND ABSORPTION COEFFICIENT (A) (1000 A 2000 HZ)	EN 13984:2004+A1:2015	α	0,20
THERMAL CONDUCTIVITY	EN 13984:2004+A1:2015	W/ (m·K)	0,15
AIRBORNE SOUND INSULATION (SURFACE MASS) (R)	EN 13986:2004+A1:2015	db	22
WATER VAPOUR PERMEABILITY DRY CUP	EN 13986:2004+A1:2015	μ	34
WATER VAPOUR PERMEABILITY WET CUP	EN 13986:2004+A1:2015	μ	23
BIOLOGICAL DURABILITY USE	EN 13986:2004+A1:2015	Class of use	1
CONTENT OF PENTACHLOROPHENOL (PCP)	EN 13986:2004+A1:2015	%	<5
FORMALDEHYDE CLASS	EN 622-1:2003	class	E1

TOLERANCE ON NOMINAL DIMENSIONS

PROPERTIES	TEST METHOD	UNITS	THICKNESSES mm
			5 - <7
THICKNESS	EN 324-1	mm	+/-0.15
LENGTH/WIDTH	EN-324-1	mm	+/- 2 mm/m max +/- 5 mm.
SQUARENESS	EN 324-2	mm/m	+/- 2 mm/m .
EDGE STRAIGHTNESS	EN-324-2	mm/m	+/-1.5 mm/m .

(*) VALUES TO BE CONSIDERED AS A ROUGH GUIDE ONLY.

These physical-mechanical values improve/comply with those established by EN 622-5:2009 European Standard, Table 3. Requirements for boards for use in dry conditions (Type MDF).

The quality of FIBRANOR IGNIFUGO NAF is endorsed by AITIM Quality Labels and CE Marking verified by AENOR.

FIBRANOR IGNIFUGO NAF meet Class E1 requirements (analysed according to EN ISO 12460-5) as defined in EN 622-1:2003 European Standard.

FIBRANOR IGNIFUGO NAF is manufactured with resins without formaldehyde.

FIBRANOR IGNIFUGO NAF is approved by the Air Resources Board of the State of California and comply with phase 2 requirements on low formaldehyde emissions and with US EPA TSCA Title VI.

(SELECT)

Non dangerous product. Adequate ergonomic techniques and IPEs must be used when handling. Dust generated in cutting, sanding, drawmilling and other processes must be extracted from the working environment with the usual procedures in the wood industry as industrial vacuum systems and IPEs use must be observed according to law.

