



FIBRAPAN IGNIFUGO E-Z -Finsa PADRON-

TECHNICAL DATA-AVERAGE VALUES

Rev: 14/12/2021

PROPERTIES	TEST METHOD	UNITS	THICKNESSES mm		
			10/12	>12/19	>19/30
DENSITY (*)	EN 323	kg/m3	830/790	790/770	770/740
INTERNAL BOND	EN 319	N/mm2	0.60	0.55	0.55
BENDING STRENGTH	EN 310	N/mm2	22	20	18
MODULUS OF ELASTICITY	EN 310	N/mm2	2500	2200	2100
THICKNESS SWELLING 24 H	EN 317	%	15	12	10
DIMENSIONAL MOVEMENT LENGTH/WIDTH	EN 318	%	0.5	0.5	0.4
DIMENSIONAL MOVEMENT TICKNESS	EN 318	%	7	7	6
SURFACE SOUNDNESS	EN 311	N/mm2	1.2	1.2	1.2
SURFACE ABSORPTION (TWO FACES)	EN 382-1	mm	> 150	> 150	> 150
MOISTURE CONTENT	EN 322	%	7+/-3	7+/-3	7+/-3
FORMALDEHYDE EMISSION	EN 717-1	ppm	≤ 0.05	≤ 0.05	≤ 0.05
REACTION TO FIRE	EN 13501-1	Euroclass	B-s1,d0	B-s1,d0	B-s1,d0
SOUND ABSORPTION COEFFICIENT (A) (250 A 500 HZ)	EN 13984:2004+A1:2015	α	0.10	0.10	0.10
SOUND ABSORPTION COEFFICIENT (A) (1000 A 2000 HZ)	EN 13984:2004+A1:2015	α	0.20	0.20	0.20
THERMAL CONDUCTIVITY	EN 13984:2004+A1:2015	W/ (m·K)	0.14	0.14	0.13
AIRBORNE SOUND INSULATION (SURFACE MASS) (R)	EN 13986:2004+A1:2015	db	25	27	29
WATER VAPOUR PERMEABILITY DRY CUP	EN 13986:2004+A1:2015	μ	30	29	28
WATER VAPOUR PERMEABILITY WET CUP	EN 13986:2004+A1:2015	μ	20	19	18
BIOLOGICAL DURABILITY USE	EN 335	Class of use	1	1	1
CONTENT OF PENTACHLOROPHENOL (PCP)	EN 13986:2004+A1:2015	ppm	< 5	< 5	< 5

TOLERANCE ON NOMINAL DIMENSIONS

PROPERTIES	TEST METHOD	UNITS	THICKNESSES mm		
			10/12	>12/19	>19/30
THICKNESS	EN 324-1	mm	+/-0.20	+/-0.20	+/-0.20
LENGTH/WIDTH	EN-324-1	mm	+/- 2	+/- 2	+/- 2
			mm/m	mm/m	mm/m
			max +/- 5 mm.	max +/- 5 mm.	max +/- 5 mm.
SQUARENESS	EN 324-2	mm/m	+/- 2 mm/m .	+/- 2 mm/m	+/- 2 mm/m
EDGE STRAIGHTNESS	EN-324-2	mm/m	+/-1.5 mm/m .	+/-1.5 mm/m	+/-1.5 mm/m

(*) VALUES TO BE CONSIDERED AS A ROUGH GUIDE ONLY.

These physical-mechanical values improve/comply with those established by EN 622-5:2009 European Standard, Table 3. Requirements for general purpose boards for use in dry conditions (type MDF).

FIBRAPAN IGNIFUGO E-Z is a low formaldehyde emission product E05 (≤ 0.05 ppm EN 717-1) and meets Class E1 requirements as defined in EN 622-1 European Standard.

FIBRAPAN IGNIFUGO E-Z bear CE Marking, certified by AENOR, number 0099/CPD/A65/0025.

Link to download:

<https://drive.google.com/file/d/0B-Xe1750UJbXUzhGV3BUOUN2QkVhNENMdHFuMkZGSUuTOEtr/view?usp=sharing>

(!) Reaction to fire classification report and field of application, link to report:

<https://drive.google.com/file/d/1cw5WWlXvQz52G3nQZ-lcfSNhGg7xOxTV/view?usp=sharing>

Individual test reports available under request.

FIBRAPAN IGNIFUGOE-Z is CARB Phase 2 and US EPA TSCA Title VI certified (Formaldehyde emission < 0.11 ppm ASTM E 1333).

Link to EPA certificate: <https://drive.google.com/file/d/0B-Xe1750UJbXWnJQbEJyT1ctYVE/view?usp=sharing>

Link to CARB P2 certificate:

https://drive.google.com/file/d/1_IId638lhosDHRw6ksvnWF4Lh4EEQgTn/view?usp=sharing

Link to quarterly atestation:

<https://drive.google.com/file/d/0B-Xe1750UJbXcIzJN0JnYmQxYIE/view?usp=sharing>

<div style='visibility:hidden;';>(SELECT)</div>

Non dangerous product. Adequate ergonomic techniques and IPEs must be used when handling. Dust generated in cutting, sanding, drawmilling and other processes

must be extracted from the working environment with the usual procedures in the wood industry as industrial vacuum systems and IPEs use must be observed according to law.
