



FINANCIERA MADERERA S.A. (FINSA)
N-550, KM 57
15890 SANTIAGO DE COMPOSTELA (A
CORUÑA)
SPAIN

DECLARATION OF PERFORMANCE N° 00229



FIBRACOLOUR AMARILLO E-Z

Manufactured at: Finsa Orember
Políg. Ind. San Cibrao das Viñas
32911 OURENSE (ESPAÑA)

TECHNICAL CLASS	INTENDED USE	AVCP*
MDF	Internal use as non structural component in dry conditions	4

*Assessment and verification of constancy of performance system according to Annex V of regulation (EU) No 305/2011

DECLARATION OF PERFORMANCE N° 00229



07/04/2021

FIBRACOLLOUR AMARILLO E-Z

FIBRACOLLOUR AMARILLO E-Z

TECHNICAL DATA-AVERAGE VALUES

Rev: 02/01/2020

PROPERTIES	TEST METHOD	UNITS	THICKNESSES mm		
			10 - 12	>12 - 19	>19 -30
DENSITY (*)	EN 323	kg/m ³	740-730	695-650	650-640
INTERNAL BOND	EN 319	N/mm ²	0.60	0.55	0.55
BENDING STRENGTH	EN 310	N/mm ²	22	20	18
MODULUS OF ELASTICITY	EN 310	N/mm ²	2500	2200	2100
THICKNESS SWELLING 24 H	EN 317	%	15	12	10
DIMENSIONAL MOVEMENT LENGTH/WIDTH	EN 318	%	0.4	0.4	0.3
DIMENSIONAL MOVEMENT TICKNESS	EN 318	%	4	4	3
SURFACE SOUNDNESS	EN 311	N/mm ²	>1.2	>1.2	>1.2
SURFACE ABSORPTION (TWO FACES)	EN 382-1	mm	>150	>150	>150
MOISTURE CONTENT	EN 322	%	7+/-3	7+/-3	7+/-3
GRIT CONTENT	ISO 3340	% Weight	≤ 0,05	≤ 0,05	≤ 0,05
FORMALDEHYDE EMISSION	EN 717-1	ppm	≤ 0,05	≤ 0,05	≤ 0,05
REACTION TO FIRE TABLA 8 EN EN 13986:2006+A1:2015	EN 13501-1	Class	D-s2,d0 (**)	D-s2,d0 (***)	D-s2,d0
SOUND ABSORPTION COEFFICIENT (A) (250 A 500 HZ)	EN 13984:2004+A1:2015	α	0.10	0.10	0.10
SOUND ABSORPTION COEFFICIENT (A) (1000 A 2000 HZ)	EN 13984:2004+A1:2015	α	0.20	0.20	0.20
THERMAL CONDUCTIVITY	EN 13984:2004+A1:2015	W/ (m·K)	0.13	0.11	0.11
AIRBORNE SOUND INSULATION (SURFACE MASS) (R)	EN 13986:2004+A1:2015	db	25	27	29
WATER VAPOUR PERMEABILITY DRY CUP	EN 13986:2004+A1:2015	μ	27	23	22
WATER VAPOUR PERMEABILITY WET CUP	EN 13986:2004+A1:2015	μ	17	14	14
BIOLOGICAL DURABILITY USE	EN 335	Class of use	1	1	1
CONTENT OF PENTACHLOROPHENOL (PCP)	EN 13986:2004+A1:2015	ppm	< 5	< 5	< 5

(*) VALUES TO BE CONSIDERED AS A ROUGH GUIDE ONLY.

(**) Mounted without an air gap behind the FIBRACOLLOUR AMARILLO E-Z. Mounted with a closed air gap not more than 22 mm behind the FIBRACOLLOUR AMARILLO E-Z classification D-s2,d2. Classification E for any other more restrictive condition. Commission Decision 2007/348/EC.

(***) Mounted without an air gap behind the FIBRACOLLOUR AMARILLO E-Z, or with a closed air gap behind the FIBRACOLLOUR AMARILLO E-Z for thicknesses equal or greater than 15mm or with an open air gap behind the FIBRACOLLOUR AMARILLO E-Z for thicknesses equal or greater than 18 mm. Mounted with a closed air gap not more than 22 mm behind the FIBRACOLLOUR AMARILLO E-Z classification D-s2,d2 in thicknesses between >12 and 18 mm. Commission Decision 2007/348/EC.

These physical-mechanical values improve/comply with those established by EN 622-5:2009 European Standard, Table 3. Requirements for boards for use in dry conditions (type MDF)

FIBRACOLLOUR AMARILLO E-Z is a low formaldehyde emission product E05 (≤ 0.05 ppm EN 717-1) and meets Class E1 requirements as defined in EN 622-1:2003 European Standard.

FIBRACOLLOUR AMARILLO E-Z is CARB Phase 2 and US EPA TSCA Title VI certified (Formaldehyde emission < 0.11 ppm ASTM E 1333).

Link to EPA certificate: <https://drive.google.com/file/d/0B-Xe1750UJbXRkstUnF5T2tLS0hNUUUh6Q29kMFNTWXI4V1U4/view?usp=sharing>

Link to CARB P2 certificate:

<https://drive.google.com/file/d/0B-Xe1750UJbXRWtPT2hGYzZyZDNqU2ZsRHY0aWc5SGJORINV/view?usp=sharing>

The performance of the reference product are in compliance with the performance declared above
This Declaration of Performance is issued under the sole responsibility of FINANCIERA MADERERA S.A. (Finsa)

Javier Portela
FINSA R&D + Quality Director

Javier Botel

