



FIBRAPAN PLUS

TECHNICAL DATA-AVERAGE VALUES

Rev: 09/12/2016

PROPERTIES	TEST METHOD	UNITS	THICKNESSES mm		
			>9/12	>12/19	>19/30
DENSITY (*)	EN 323	kg/m ³	760/750	750/725	725/700
INTERNAL BOND	EN 319	N/mm ²	0,90	0,80	0,75
BENDING STRENGTH	EN 310	N/mm ²	25	25	23
MODULUS OF ELASTICITY	EN 310	N/mm ²	2800	2800	2500
THICKNESS SWELLING 24 H	EN 317	%	15	12	10
DIMENSIONAL MOVEMENT LENGTH/WIDTH	EN 318	%	0,4	0,4	0,3
DIMENSIONAL MOVEMENT THICKNESS	EN 318	%	6	6	5
SURFACE SOUNDNESS	EN 311	N/mm ²	1,2	1,2	1,2
SURFACE ABSORPTION (TWO FACES)	EN 382-1	mm	> 150	> 150	> 150
MOISTURE CONTENT	EN 322	%	7+/-3	7+/-3	7+/-3
GRIT CONTENT	ISO 3340	% Weight	≤ 0,05	≤ 0,05	≤ 0,05
FORMALDEHYDE CONTENT	EN ISO 12460-5	mg/100 g	≤ 8	≤ 8	≤ 8
REACTION TO FIRE TABLA EN 13986:2004+A1:2015 I	EN 13501-1	Class	D- s2,d0(**)	D- s2,d0(***)	D-s2,d0
SOUND ABSORPTION COEFFICIENT (A) (250 A 500 HZ)	EN 13984:2004+A1:2015	α	0.10	0.10	0.10
SOUND ABSORPTION COEFFICIENT (A) (1000 A 2000 HZ)	EN 13984:2004+A1:2015	α	0.20	0.20	0.20
THERMAL CONDUCTIVITY	EN 13984:2004+A1:2015	W/ (m·K)	0.14	0.13	0.13
AIRBORNE SOUND INSULATION (SURFACE MASS) (R)	EN 13986:2004+A1:2015	db	27	28	31
WATER VAPOUR PERMEABILITY DRY CUP	EN 13986:2004+A1:2015	μ	28	26	25
WATER VAPOUR PERMEABILITY WET CUP	EN 13986:2004+A1:2015	μ	18	17	16
BIOLOGICAL DURABILITY USE	EN 13986:2004+A1:2015	Class of use	1	1	1
CONTENT OF PENTACHLOROPHENOL (PCP)	EN 13986:2004+A1:2015	%	< 5	< 5	< 5

TOLERANCE ON NOMINAL DIMENSIONS

PROPERTIES	TEST METHOD	UNITS	THICKNESSES mm		
			>9/12	>12/19	>19/30
THICKNESS	EN 324-1	mm	+/-0,2	+/-0,2	+/-0,3
LENGTH/WIDTH	EN-324-1	mm	+/- 2	+/- 2	+/- 2
			mm/m, máx +/- 5 mm.	mm/m, máx +/- 5 mm.	mm/m, máx +/- 5 mm.
SQUARENESS	EN 324-2	mm/m	+/- 2	+/- 2	+/- 2
EDGE STRAIGHTNESS	EN-324-2	mm/m	+/-1,5	+/-1,5	+/-1,5

(*) VALUES TO BE CONSIDERED AS A ROUGH GUIDE ONLY.

(**) Mounted without an air gap behind the FIBRAPAN PLUS. Mounted with a closed air gap not more than 22 mm behind the FIBRAPAN PLUS classification D-s2,d2. Classification E for any other less restrictive condition. Commission Decision 2007/348/EC.

(***) Mounted without an air gap behind the FIBRAPAN PLUS, or with a closed air gap behind the FIBRAPAN PLUS for thicknesses equal or greater than 15mm or with an open air gap behind the FIBRAPAN PLUS for thicknesses equal or greater than 18 mm. Mounted with a closed air gap not more than 22 mm behind the FIBRAPAN PLUS classification D-s2,d2 in thicknesses between >12 mm and 18 mm. Commission Decision 2007/348/EC.

These physical-mechanical values improve/comply with those established by EN 622-5:2009 European Standard, Table 3. Requirements for boards for use in dry conditions (type MDF)

FIBRAPAN PLUS meets Class E1 requirements (analysed according to EN ISO 12460-5) as defined in EN 622-1:2003 European Standard.

FIBRAPAN PLUS is endorsed by AITIM Quality Labels.

(SELECT)

Non dangerous product. Adequate ergonomic techniques and IPEs must be used when handling. Dust generated in cutting, sanding, drawmilling and other processes must be extracted from the working environment with the usual procedures in the wood industry as industrial vacuum systems and IPEs use must be observed according to law.

