



FINANCIERA MADERERA S.A. (FINSA)
N-550, KM 57
15890 SANTIAGO DE COMPOSTELA (A
CORUÑA)
SPAIN

DECLARATION OF PERFORMANCE N° 00234



23/01/2019

FIMAPLAST H E-Z

Manufactured at:

PRODUCT TYPE	INTENDED USE	AVCP*
P3	Internal use as nonstructural component in humid conditions	4

*Assessment and verification of constancy of performance system according to Annex V of regulation (EU) No 305/2011

DECLARATION OF PERFORMANCE N° 00234



23/01/2019

FIMAPLAST H E-Z

FIMAPLAST H E-Z

TECHNICAL DATA-AVERAGE VALUES

Rev: 23/01/2019

PROPERTIES	TEST METHOD	UNITS	THICKNESSES mm				
			8/13	>13/20	>20/25	>25/32	>32/40
DENSITY (*)	EN 323	kg/m ³	720/680	675/650	640/625	600	600
INTERNAL BOND	EN 319	N/mm ²	0,45	0,45	0,40	0,35	0,30
BENDING STRENGTH	EN 310	N/mm ²	15	14	12	11	9
MODULUS OF ELASTICITY	EN 310	N/mm ²	2050	1950	1850	1700	1550
THICKNESS SWELLING 24 H	EN 317	%	17	14	13	13	12
MOISTURE CONTENT	EN 322	%	8+/-3	8+/-3	8+/-3	8+/-3	8+/-3
REACTION TO FIRE TABLA 8 EN 13986:2004+A1:2015 I	EN 13501-1	Class	D-s2,d0 (**)	D-s2,d0 (***)	D-s2,d0	D-s2,d0	D-s2,d0
REACTION TO FIRE TABLA 8 EN 13986:2004+A1:2015 I	EN 13501-1	Class	Dfl-s1 (****)	Dfl-s1	Dfl-s1	Dfl-s1	Dfl-s1
SWELLING IN THICKNESS AFTER CYCLIC TEST (V313)	EN 321 / EN 317	%	14	13	12	12	11
INTERNAL BOND AFTER CYCLIC TEST (V313)	EN 321 / EN 319	N/mm ²	0,15	0,13	0,12	0,10	0,09
SOUND ABSORPTION COEFFICIENT (A) (250 A 500 HZ)	EN 13984:2004+A1:2015	α	0.10	0.10	0.10	0.10	0.10
SOUND ABSORPTION COEFFICIENT (A) (1000 A 2000 HZ)	EN 13984:2004+A1:2015	α	0.25	0.25	0.25	0.25	0.25
THERMAL CONDUCTIVITY	EN 13984:2004+A1:2015	W/ (m·K)	0.14	0.14	0.13	0.12	0.12
AIRBORNE SOUND INSULATION (SURFACE MASS) (R)	EN 13986:2004+A1:2015	db	24	27	29	30	31
WATER VAPOUR PERMEABILITY DRY CUP	EN 13986:2004+A1:2015	μ	50	50	50	50	50
WATER VAPOUR PERMEABILITY WET CUP	EN 13986:2004+A1:2015	μ	16	16	16	16	15
BIOLOGICAL DURABILITY USE	EN 13986:2004+A1:2015	Class of use	1 & 2	1 & 2	1 & 2	1 & 2	1 & 2
CONTENT OF PENTACHLOROPHENOL (PCP)	EN 13986:2004+A1:2015	%	<5	<5	<5	<5	<5

(*) VALUES TO BE CONSIDERED AS A ROUGH GUIDE ONLY.

(**) Minimum thickness 9mm. Mounted without an air gap behind the FIMAPLAST H E-Z. Mounted with a closed air gap not more than 22 mm behind the FIMAPLAST H E-Z classification D-s2,d2. Classification E for any other more restrictive condition. Commission Decision 2007/348/EC.

(***) Mounted without an air gap behind the FIMAPLAST H E-Z, or with a closed air gap behind the FIMAPLAST H E-Z for thicknesses equal or greater than 15mm or with an open air gap behind the FIMAPLAST H E-Z for thicknesses equal or greater than 18 mm. Mounted with a closed air gap not more than 22 mm behind the FIMAPLAST H E-Z classification D-s2,d2 in thicknesses between 10 and 18 mm. Commission Decision 2007/348/EC

(****) Minimum thickness 9 mm

(v*) Thickness ≥15 mm and balanced recoverings.

These physical-mechanical values improve/comply with the P3 classification established in EN 312:2010 European Standard, Tables 4 and 5. Non-structural boards used in humid conditions (Type P3). Requirements for the specified mechanical and swelling properties. Requirements for moisture resistance (Option 1).

FIMAPLAST H E-Z comply with CARB Phase 2 and US EPA TSCA Title VI requirements.

FIMAPLAST H E-Z is endorsed by AITIM Quality Label.

HANDLING/STORAGE:

It must always be stored under cover and on a flat surface.
65% of humidity is the ideal condition for its storage, dryer or more moist environments should be avoided.
It must never be in direct contact with water.
Blocks must always be lined up with the vertical.
Never pile up more than 4 heights.
If the packaging is damaged during its handling, it must be packed again so the product is correctly preserved.

If the piling-up conditions or the changes in moisture or temperature above mentioned are not respected in the warehouses or the processing areas, they may cause irreversible deformations and warpings.

Javier Portela
FINSA R&D + Quality Director
Santiago de Compostela 23/01/2019



The image shows a handwritten signature in blue ink that reads "Javier Portela". Below the signature is a horizontal line. To the right of the signature is a circular blue stamp. The stamp contains the text "FINANCIERA MADERERA, S.A." at the top and "SANTIAGO" at the bottom, with two small stars on either side of the bottom text.